

Product Datasheet

Euroroof Self-Adhesive Venting Underlay

Sheet No: PDS-RBM024 Issued: 28/02/2025

Pages: 1 of 1

Description

Euroroof Self Adhesive Venting Underlay is a polyester reinforced, special modified bitumen underlayer, for use as a self-adhesive base layer in built- up roofing systems, in both new build and refurbishment projects. The special perforated PP fleece on the underside facilitates a partial bonding to the approved insulation which enables any trapped gases, air or moisture to dissipate evenly.

Finish

Membranes of this range have an underside surface finish made of a removable silicone film on the perforated PP fleece, while the top side surface finish is composed of thermofusible polyethylene PE film. Rolls are provided with a side selvedge covered with a siliconised removable band in PE.

Application

All surfaces to receive membrane must be clean and dry. Prime the substrate with Euroroof SA Primer. Install the Euroroof Self Adhesive Venting Underlay with 75mm side and 150mm end laps, by removing the release film and firmly pressure rolling the surface to achieve a continuous bond across the full width of the membrane. Ensure that the membrane is accurately aligned, including overlaps, before removing the release film, and that it does not move as the film is removed. The main field sheet should be pressure rolled with a weighted roller to ensure full contact of the membranes; the addition of hot air may be required to achieve full adhesion in colder conditions.

The side laps (75mm) and head laps (150mm) must be hot air welded and pressure rolled with a long or medium handled 15kg roller. All laps must have a visible bleed of bitumen.

Substrate/s must be even and free from any irregularities that may compromise the bond. Undertake an adhesion test to establish a full bond can be obtained using the self-adhesive membrane to the primed substrate. Please contact Alumasc technical services for further guidance if the bond strength is unsatisfactory.

Storage - Store upright in a clean, dry location, away from heat sources. The product must be stored at between 10°C and 24°C for 24 hours prior to use.

Product Data

Thickness	2.0mm
Width	1.0m
Length	15.0m
Weight	2.2 kg/m2
Weight per roll	33 kg

Performance Data

Tensile Strength – longitudinal	695 N/50mm
Tensile Strength – transverse	505 N/50mm
Elongation at break – longitudinal	40%
Softening point	100°C
Shelf Life	12 months
Cold Flexibility	-15°C

Health & Safety

Safety Data Sheets are available upon request and can also be downloaded directly from www.alumascroofing.com.

Technical Support

Technical advice is available from Alumasc Technical Services at:

Telephone: +44 (0) 1744 648400

Email: technical@alumascroofing.com

The company pursues a policy of constant product development and information contained in this publication is therefore subject to change without notice. The customer is responsible for ensuring that each product is fit for its intended purpose and that the conditions for use are suitable. All quoted data is nominal and subject to production tolerances.