

Product Data Sheet

Eurorooft PVC Primer

Sheet No: PDS-CAL002

Issued: June 2026

Pages: 1 of 1

Description

Eurorooft PVC Primer is a single-component, cold-applied primer based on polyurethane technology. It is specifically designed to prepare and promote adhesion to existing PVC single-ply membrane systems prior to the application of compatible coatings or waterproofing systems.

Surface Preparation

All surfaces must be clean, dry, and free from contaminants including dust, dirt, grease, oils, laitance, biological growth, or any loosely adhered materials that may impair adhesion.

Where contamination is present, scrub all contaminated surfaces with soapy water and rinse down with clean water.

Application

Apply Eurorooft PVC Primer uniformly in a single coat using a brush or short-pile roller, ensuring full and even coverage. Typical coverage rate: 8 – 12 m² per litre, depending on the condition, porosity, and texture of the substrate.

Allow the primer to fully cure before applying subsequent coatings. Drying time will vary depending on ambient temperature, humidity, and ventilation conditions.

Product Data

Packaging	5l drum
Colour(s)	Amber
Solids content	8 - 13%
Coverage rate	8 – 12m ² per litre
Cure time	2-6 hours, subject to ambient temperatures
Application temperature	5 - 25°C - 3°C above the dew point
Storage temperature	5 - 25°C - do not store in direct sunlight
Shelf-life	12 months.

Health & Safety

Safety Data Sheets are available upon request and can also be downloaded directly from www.alumascroofing.com.

Technical Support

Technical advice is available from Alumasc Technical Services at:

Telephone: +44 (0)1744 648400

Email: technical@alumascroofing.com

The company pursues a policy of constant product development and information contained in this publication is therefore subject to change without notice. The customer is responsible for ensuring that each product is fit for its intended purpose and that the conditions for use are suitable. All quoted data is nominal and subject to production tolerances.