

Description

Caltech FCP Universal Primer is a multi-functional primer for use with Alumasc's Caltech FCP System.

Use

Caltech FCP Universal Primer is suitable for use on surfaces including felt, asphalt, single ply membranes (subject to adhesion tests), plywood, OSB3 and concrete.

Application

For preparation and application guidance, please consult Alumasc specification.

Catalysing

- Stir the Caltech FCP Universal Primer thoroughly, mixing from top to bottom.
- Add the additive as required, and the Catalyst in the form of level scoops (using the scoop provided).
- Thoroughly mix the resin and catalyst using a slow speed mechanical agitator until the catalyst has been evenly distributed, minimum 2 minutes.

Temperature	3°C - 10°C	10°C - 19°C	20°C - 24°C	25- 30°C
Catalyst %	4%	3%	2%	2%
Additive	Accelerator required below 4 °C	N/A	N/A	N/A
No. of scoops per 5l	20	15	10	10
No. of scoops per 10l	40	30	20	20

Product Data

Packaging	5 & 10 litre drums
Colour(s)	White
Coverage	4-5m ² /l
Typical Cure time	30-60 mins
Application Temperature	5°C* – 30°C (Minimum temperature of 1°C, with the addition of Caltech FCP Accelerator)
Storage	Observe label precautions. Store in a dry, cool and well-ventilated area. Keep away from heat and direct sunlight. Keep container tightly closed. Keep away from sources of ignition. No smoking. Prevent unauthorised access. Containers that have been opened must be carefully re-sealed and kept upright to prevent leakage.
Shelf-life	12 months if stored as above.

*Coverage is approximate and may be affected by porosity and surface-type.

Health & Safety

Copies of Alumasc Safety Data Sheets can be downloaded from the Alumasc Roofing [website](https://www.alumascroofing.com/downloads).