

Description

Eurorooft Torch-On Cap Sheet is an APP modified, mineral surfaced bitumen membrane with glass/polyester reinforcement. It is available in a Charcoal colour finish, with other colours available to order.

Use

Reinforced cap sheet for use in built-up roofing systems on both new-build and refurbishment projects.

Approvals

British Board of Agrément Certificate No 24/7275.

Application

Fully bonded by torch application.

- Laps can be sealed either by torch application or hot-air welding.
- Lap sizes: 100mm side, 150mm end, pressure rolled simultaneously with a long-handled 15kg lap roller.
- Position the membrane starting from the lowest point of the roof.
- Membrane sheets must be staggered, avoiding any overlaps against the fall.
- Pre-cut the lower corner of the end of each roll at 45° where it will be overlapped by the end lap of the next roll.
- Apply the second layer of membrane astride and over the first layer (always in the same direction and approximately 1/4 of its length from the previous sheet).
- Heat evenly across the surface, maintaining a liquid bitumen mass in front of the roll (saturating any superficial porosity).

Fire Rating

Classified as BROOF(t4) in accordance with BS EN 13501-5 following testing to BS EN 1187: Test 4. This classification permits unrestricted use under the Building Regulations when installed as part of the tested roof assembly.

Storage

Store upright in a clean, dry location, away from heat sources.

Product Data

Thickness	4mm
Width	1m
Length	7.5m
Weight	5.1 kg/m ²
Weight per roll	38 kg

All dimensions are nominal and subject to manufacturing tolerances.

Performance Data

Tensile Strength – longitudinal	>735 N/50mm
Tensile Strength – transverse	>530 N/50mm
Elongation at break – longitudinal	40%
Softening point	120°C
Cold bend	-15°C

Health & Safety

Copies of Alumasc Safety Data Sheets can be downloaded from the Alumasc Roofing [website](#).