

Description

Hydrogard 40M-AR is a polyester reinforced, oxidised bituminous protection sheet, with a sanded finish on the underside and a black mineral surfaced upper side.

Use

As a protection sheet for Hydrotech Monolithic Membrane 6125.

Application

Laid directly into the second coat of Hydrotech, with torch-sealed 75mm side and end laps.

Do not seal the overlaps with Hydrotech membrane.

Storage

Store upright in a clean, dry location, away from heat sources.

Product Data

Thickness	3.5mm
Width	1m
Length	10m
Weight	3.5 kg/m ²
Weight per roll	35 kg

All dimensions are nominal and subject to manufacturing tolerances.

Performance Data

Tensile Strength – longitudinal	>500 N/50mm
Tensile Strength – transverse	>350 N/50mm
Elongation at break – longitudinal	40%
Softening point	130°C
Cold flex	-10°C

Health & Safety

Copies of Alumasc Safety Data Sheets can be downloaded from the Alumasc Roofing [website](#).